

ADIT SAMPLING: SIGNIFICANT RESULTS

		Width (m)	Au g/t	Ag g/t	Cu %
<u>Crosscut 1S:</u>	West Wall	15.45	1.31	55.3	1.53
	East Wall	14.0	5.17	78.7	2.06
<u>Crosscut 2S:</u>	West Wall	8.20	1.11	45.5	1.51
	East Wall	9.70	1.89	103.0	2.14
<u>Crosscut 3S:</u>	West Wall	3.80	4.60	155.4	2.01
	East Wall	4.30	9.51	581.9	3.93
	East wall	1.00	108.44	1154.0	4.83
	East wall	0.30	50.21	629.0	3.47
	East wall	1.50	58.84	595.0	4.24
<u>Crosscut 4S:</u>	West Wall	3.60	2.27	47.1	1.44
	East Wall	5.30	3.71	49.9	1.66
<u>SW Crosscut:</u>	West Wall	5.80	0.95	18.4	0.79
	East Wall	7.70	1.47	39.3	0.77
<u>Crosscut 315 N:</u>	West Wall	18.90	0.60	18.1	0.79
	East Wall	12.30	0.67	18.6	0.79