

Table ii: Base metal recoveries and grades via various process options

Process	Copper (%)		Zinc (%)		Lead (%)	
	Rec'y	Grade	Rec'y	Grade	Rec'y	Grade
CVD Ro/Sc/CI to 10% mass	+/-18	+/-2.7	+/-18	+/-3.4	+/-75	+/-11
CVD Ro/Sc/CI to 20% mass	+/-35	+/-3.0	+/-3.0	+/-3.5	+/-80	+/-6
CVD Ro/Sc to 37% mass	63	2.5	62	3.0	84	3.0
CVD Ro/Sc, float tails 44% mass	98	3.1	98	4.2	94	2.9
CVD Ro/Sc, float tails 47% mass	98	3.0	98	4.0	94	2.8

**Note:** Recoveries and grades at 10 and 20% mass yield have been interpolated from charts. Note that copper and zinc grades from gravity processing increase with mass yield as lead is depleted (thus no longer displacing Cu & Zn downstream).