

Laterit-Horizont	Mittlere Mächtigkeit (m)	% Ni	% Co	% Fe
Eisenlaterit	1.08	0.69	0.05	42.28
Limonit	2.16	1.09	0.11	43.30
Saprolit	5.49	1.29	0.03	12.62