

Die Ergebnisse der Oberflächenproben bei Mamulique lauten wie folgt:

Probe #	Probenart und Breite	Ag g/t	Pb %	Zn %
MM01	Ader 20 cm	185	15.9	7.52
MM02	Ader 5 cm	314	>20.0	6.51
MM02A	Ader 11 cm	257	>20.0	6.98
MM03	Ader 5 cm	368	>20.0	23.5
MM04	Ader 30 cm	49.7	6.24	0.63
MM05	Ader 10 cm	22.7	0.76	14.85
MM06	Ader 10 cm	107	17.9	14.4
MM07	Abgang Mine Santo Niño	30.3	0.83	4.71
MM08	Abgang Mine Santo Niño	11	1	18.15
MM09	Abgang Mine Santo Niño	62.2	1.58	20.7
MM11	Ader 12 cm	381	>20.0	2.44
MM12	Ader 13 cm	98	17.1	19.3
MM13	Ader 12 cm	125	10.8	30
MM14	Ader 30 cm	4	0.5	0.23
MM15	Ader 40 cm	0.8	0.07	3.8
MM16	Abgang Mine La Victoria	64.6	6.86	0.21
MM17	Ader 20 cm	12	1.25	1.88
MM18	Ader 25 cm	44.1	8.41	10.35