

## GERMAN

Bohrloch (Azimut, Neigung)	Von (m)	Bis (m)	Länge (m)	Ag (g/t)	Cu (%)	Au (g/t)	Ag-Äq. (g/t) *
LJ-DD10-01 (360, - 50)	44.2	46.2	2.0	80.8	0.55	0.06	144.1
	<b>60.2</b>	<b>75.4</b>	<b>15.2</b>	<b>75.3</b>	<b>0.58</b>	<b>0.45</b>	<b>161.4</b>
einschl.	74.4	75.4	1.0	382.0	2.46	0.15	659.4
	110.4	117.6	7.3	91.8	0.98	0.22	210.3
	129.0	139.8	10.8	31.8	0.52	0.17	97.4
	<b>152.7</b>	<b>164.8</b>	<b>12.1</b>	<b>126.7</b>	<b>1.07</b>	<b>0.26</b>	<b>257.1</b>
einschl.	<b>152.7</b>	<b>155.8</b>	<b>3.1</b>	<b>376.7</b>	<b>2.57</b>	<b>0.58</b>	<b>687.7</b>
LJ-DD10-02 (45, - 50)	<b>69.8</b>	<b>73.2</b>	<b>3.4</b>	<b>171.8</b>	<b>2.62</b>	<b>0.14</b>	<b>466.3</b>
	<b>190.4</b>	<b>197.2</b>	<b>6.8</b>	<b>192.3</b>	<b>0.90</b>	<b>0.40</b>	<b>311.0</b>
einschl.	194.2	196.1	1.9	294.2	2.00	0.30	528.6
LJ-DD10-03 (360, - 90)	52.9	53.7	0.8	196.7	1.28	0.04	339.1
	<b>137.5</b>	<b>151.1</b>	<b>13.5</b>	<b>41.2</b>	<b>0.45</b>	<b>0.53</b>	<b>117.1</b>
LJ-DD10-04 (360, -50)	23.5	24.6	1.1	41.5	0.74	0.11	128.2
	31.6	35.7	4.1	79.2	0.23	0.13	110.9
	<b>40.4</b>	<b>59.6</b>	<b>19.2</b>	<b>156.5</b>	<b>0.82</b>	<b>0.18</b>	<b>255.5</b>

1

einschl.	<b>48.6</b>	<b>58.4</b>	<b>9.8</b>	<b>241.4</b>	<b>1.36</b>	<b>0.27</b>	<b>404.1</b>
	77.2	79.3	2.1	164.9	1.44	0.42	343.9
	89.7	90.7	1.0	95.0	0.37	0.07	139.1
	127.6	128.7	1.1	45.3	1.07	0.38	181.7
LJ-DD10-05a (360, - 90)	167.2	176.2	9.0	19.3	0.02	0.22	32.5
LJ-DD-10-06 (360, -50)	111.2	113.2	2.0	54.8	0.53	0.06	115.9
LJ DD10-07 (135, -50)	<b>86.2</b>	<b>94.2</b>	<b>8.0</b>	<b>101.8</b>	<b>0.83</b>	<b>0.27</b>	<b>206.4</b>
einschl.	91.4	92.6	1.3	412.0	3.47	0.10	797.7
LJ DD10-08 (360, -90)	24.3	31.4	7.1	48.5	0.56	0.20	119.5
	46.4	49.4	3.0	20.0	0.04	3.35	174.0
	61.4	80.0	18.6	22.7	0.22	0.14	54.2
	87.5	90.0	2.5	68.0	0.83	0.04	160.6
LJ DD10-09 (360, -90)	21.0	27.4	6.4	37.4	0.15	0.72	89.9
	54.4	62.4	8.0	68.4	0.20	0.25	102.8
	<b>74.4</b>	<b>93.5</b>	<b>19.2</b>	<b>90.5</b>	<b>0.27</b>	<b>0.19</b>	<b>129.6</b>
einschl.	74.4	78.0	3.6	259.4	0.40	0.10	308.3
LJ DD10-10 (180, -50)	36.0	50.0	14.0	36.2	0.32	0.10	76.3
	55.0	57.0	2.0	91.7	0.71	0.03	171.1
	<b>65.0</b>	<b>92.0</b>	<b>27.0</b>	<b>47.5</b>	<b>0.48</b>	<b>0.15</b>	<b>107.7</b>
	101.0	107.0	6.0	31.2	0.40	1.15	132.5

\* Silberäquivalent basiert auf einer metallurgischen Gewinnungsrate von 100 % und Preisrelationen von 6,25:1 (Silber-Kupfer) bzw. 50:1 (Gold-Silber).

## ENGLISH

Hole (Azimuth, Dip)	From (m)	To (m)	Length (m)	Ag (gpt)	Cu (%)	Au (gpt)	Ag (g/t) equiv. *
IJ-DD10-01 (360, - 50)	44.2	46.2	2.0	80.8	0.55	0.06	144.1
	<b>60.2</b>	<b>75.4</b>	<b>15.2</b>	<b>75.3</b>	<b>0.58</b>	<b>0.45</b>	<b>161.4</b>
includes	74.4	75.4	1.0	382.0	2.46	0.15	659.4
	110.4	117.6	7.3	91.8	0.98	0.22	210.3
	129.0	139.8	10.8	31.8	0.52	0.17	97.4
	<b>152.7</b>	<b>164.8</b>	<b>12.1</b>	<b>126.7</b>	<b>1.07</b>	<b>0.26</b>	<b>257.1</b>
includes	<b>152.7</b>	<b>155.8</b>	<b>3.1</b>	<b>376.7</b>	<b>2.57</b>	<b>0.58</b>	<b>687.7</b>
IJ-DD10-02 (45, - 50)	<b>69.8</b>	<b>73.2</b>	<b>3.4</b>	<b>171.8</b>	<b>2.62</b>	<b>0.14</b>	<b>466.3</b>
	<b>190.4</b>	<b>197.2</b>	<b>6.8</b>	<b>192.3</b>	<b>0.90</b>	<b>0.40</b>	<b>311.0</b>
includes	194.2	196.1	1.9	294.2	2.00	0.30	528.6
IJ-DD10-03 (360, - 90)	52.9	53.7	0.8	196.7	1.28	0.04	339.1
	<b>137.5</b>	<b>151.1</b>	<b>13.5</b>	<b>41.2</b>	<b>0.45</b>	<b>0.53</b>	<b>117.1</b>
IJ-DD10-04 (360, -50)	23.5	24.6	1.1	41.5	0.74	0.11	128.2
	31.6	35.7	4.1	79.2	0.23	0.13	110.9
	<b>40.4</b>	<b>59.6</b>	<b>19.2</b>	<b>156.5</b>	<b>0.82</b>	<b>0.18</b>	<b>255.5</b>

1

includes	<b>48.6</b>	<b>58.4</b>	<b>9.8</b>	<b>241.4</b>	<b>1.36</b>	<b>0.27</b>	<b>404.1</b>
	77.2	79.3	2.1	164.9	1.44	0.42	343.9
	89.7	90.7	1.0	95.0	0.37	0.07	139.1
	127.6	128.7	1.1	45.3	1.07	0.38	181.7
IJ-DD10-05a (360, - 90)	167.2	176.2	9.0	19.3	0.02	0.22	32.5
IJ-DD-10-06 (360, -50)	111.2	113.2	2.0	54.8	0.53	0.06	115.9
IJ DD10-07 (135, -50)	<b>86.2</b>	<b>94.2</b>	<b>8.0</b>	<b>101.8</b>	<b>0.83</b>	<b>0.27</b>	<b>206.4</b>
includes	91.4	92.6	1.3	412.0	3.47	0.10	797.7
IJ DD10-08 (360, -90)	24.3	31.4	7.1	48.5	0.56	0.20	119.5
	46.4	49.4	3.0	20.0	0.04	3.35	174.0
	61.4	80.0	18.6	22.7	0.22	0.14	54.2
	87.5	90.0	2.5	68.0	0.83	0.04	160.6
IJ DD10-09 (360, -90)	21.0	27.4	6.4	37.4	0.15	0.72	89.9
	54.4	62.4	8.0	68.4	0.20	0.25	102.8
	<b>74.4</b>	<b>93.5</b>	<b>19.2</b>	<b>90.5</b>	<b>0.27</b>	<b>0.19</b>	<b>129.6</b>

includes	74.4	78.0	3.6	259.4	0.40	0.10	308.3
LJ DD10-10 (180, -50)	36.0	50.0	14.0	36.2	0.32	0.10	76.3
	55.0	57.0	2.0	91.7	0.71	0.03	171.1
	<b>65.0</b>	<b>92.0</b>	<b>27.0</b>	<b>47.5</b>	<b>0.48</b>	<b>0.15</b>	<b>107.7</b>
	101.0	107.0	6.0	31.2	0.40	1.15	132.5

\*Ag equivalent is based on 100% metallurgical recovery and price ratios of 6.25:1-Ag:Cu and 50:1-Au:Ag.