

Loch Nummer	Bauxit Abschnitt		Bx Mächtigkeit Stripping		% SiO2 TiO2 Al2O3 Fe2O3 LOI				
	von m	bis m	m	Ratio	SiO2	TiO2	Al2O3	Fe2O3	LOI
WCSD029	37.19	41.11	3.92	9.5	3.83	2.59	60.95	0.80	31.35
WCSD030	46.67	51.26	4.59	10.2	6.36	2.15	60.46	0.60	30.08
WCSD043	20.98	26.73	5.75	3.6	4.43	1.91	63.20	0.83	29.24
WCSD049	42.99	47.41	4.42	9.7	8.29	2.19	58.62	1.75	28.87
WCSD050	29.10	33.40	4.30	6.8	6.33	2.06	59.66	0.96	30.44
WCSD051	37.82	41.65	3.83	9.9	8.33	1.98	59.80	0.62	29.04
WCSD056	39.65	45.82	6.17	6.4	5.76	2.34	61.00	1.14	29.24
WCSD062	42.57	47.00	4.43	9.6	5.34	1.96	62.39	1.27	28.64
WCSD069	37.22	42.10	4.88	7.6	6.14	2.00	60.29	0.59	30.59
WCSD070	35.24	38.07	2.83	12.5	10.14	2.09	58.08	0.57	28.74
WCSD083	34.34	39.70	5.36	6.4	3.85	2.63	59.12	2.57	31.20
WCSD084	46.13	51.35	5.22	8.8	7.49	2.61	58.11	1.07	30.18
WCSD085	51.13	56.26	5.13	10.0	6.06	2.24	59.96	0.61	30.70
WCSD086	53.13	57.49	4.36	12.19	3.04	2.61	61.22	0.76	31.89
WCSD087	48.65	55.64	6.99	7.0	5.52	2.49	59.95	0.69	30.95
WCSD088	42.25	49.07	6.82	6.2	4.50	2.41	60.59	0.71	31.47
WCSD089	32.69	36.82	4.13	7.9	5.56	2.46	59.92	0.57	31.08
WCSD092	48.66	54.04	5.38	9.0	4.84	2.33	60.67	1.17	30.42
WCSD093	53.65	58.75	5.10	10.5	9.43	2.52	57.90	0.85	28.8
WCSD095	37.91	41.55	3.64	10.41	5.28	2.30	60.73	0.63	30.76
WCSD096	31.27	35.00	3.73	8.38	5.92	2.17	59.94	0.56	30.98
WCSD098	43.68	50.18	6.50	6.72	3.68	2.67	61.12	2.09	30.02
WCSD102	35.22	38.62	3.40	10.36	10.76	1.90	58.39	0.96	27.62
WCSD103	27.04	31.85	4.81	5.62	2.11	2.17	62.74	0.83	31.67
WCSD104	21.60	27.05	5.45	3.96	6.60	2.39	59.35	0.79	30.22
WCSD105	31.99	38.36	6.37	5.02	5.29	2.52	60.08	1.00	30.73
WCSD106	38.08	41.25	3.17	12.01	6.10	2.19	61.14	0.88	29.44
Durchschnitt	38.77	43.61	4.84	8.38	5.78	2.32	60.26	0.99	30.23

